

ABSTRACT

- A method of regenerating an ion exchange resin, comprising the steps of packing a used ion exchange resin in a regeneration tower; and repeating at least
- 5 twice a step comprising passing an aqueous solution of regenerant through the regeneration tower downward from a top part of the regeneration tower and thereafter passing ultra-pure water through the regeneration tower upward from a bottom of the regeneration tower. This
- 10 method enables regenerating an ion exchange resin efficiently and homogeneously without mixing of the regenerant into ion exchange resin towers for purification.